



CIM 800

HIGH PERFORMANCE COATINGS AND LININGS

COVERAGE CHART — MIXED GALLONS

Dry Thickness (mils)	Wet Thickness (mils)	Gal/SF	SF/Gal	Dry Thickness (mils)	Wet Thickness (mils)	Gal/SF	SF/Gal
20	23	0.015	69	17	20	0.012	80
25	29	0.018	55	21	25	0.016	64
30	35	0.022	46	26	30	0.019	53
35	41	0.025	39	30	35	0.022	46
40	47	0.029	34	34	40	0.025	40
45	53	0.033	31	39	45	0.028	36
50	58	0.036	27	43	50	0.031	32
55	64	0.040	25	47	55	0.034	29
60	70	0.044	23	51	60	0.037	27
65	76	0.047	21	56	65	0.041	25
70	82	0.051	20	60	70	0.044	23
75	88	0.055	18	64	75	0.047	21
80	93	0.058	17	69	80	0.050	20
85	99	0.062	16	73	85	0.053	19
90	105	0.066	15	77	90	0.056	18
95	111	0.069	14	81	95	0.059	17
100	117	0.073	14	86	100	0.062	16
105	123	0.076	13	90	105	0.065	15
110	128	0.080	12	94	110	0.069	15
115	134	0.084	12	99	115	0.072	14
120	140	0.087	11	103	120	0.075	13
125	146	0.091	11	107	125	0.078	13

COVERAGE FORMULAS

$$\text{Gallons Required} = \frac{\text{Theoretical Wet Film Thickness (Mils)} \times \text{Sq.Ft. To Be Covered}}{1604} = \frac{\text{Theoretical Dry Film Thickness (Mils)} \times \text{Sq.Ft. To Be Covered}}{1374}$$

1 MIL = .001 of an inch

Coverages are theoretical and do not account for waste, spillage, irregular surfaces, or application technique.

CIM BONDING AGENT

Porous Surface 1 gallon = 300 sq.ft. or .00333 gal/sq.ft.

Non Porous Surface 1 gallon = 600 sq.ft. or .00166 gal/sq.ft.

